

Magneto- and Electrotransport Properties of

$\text{Nd}_{0.67}\text{Sr}_{0.33}\text{Mn}_{1-x}\text{Fe}_x\text{O}_3$ ($x = 0.00, 0.05$)

Chang Yoke Ling^{a*} C. K. Ong^a

^a*Department of Physics, Center for Superconducting and Magnetic Materials, National University of Singapore, 2 Science Drive 3, 117542 Singapore, Singapore*

Abstract

Simultaneous studies on the magnetic and electrotransport properties of $\text{Nd}_{0.67}\text{Sr}_{0.33}\text{Mn}_{1-x}\text{Fe}_x\text{O}_3$ polycrystalline bulk and epitaxial thin films ($x = 0.00$ and 0.05) have been carried out. A magnetoresistance (MR) as high as $\sim 33\%$ is observed for $\text{Nd}_{0.67}\text{Sr}_{0.33}\text{MnO}_3$ bulk at the metal-insulator transition (MIT) temperature (T_p) of 273 K in a magnetic field ($\mathbf{H}$) of 10 kOe. Fe substitution at Mn sites reduces the ferromagnetic (FM) ordering temperature (T_c) and leads to an overall increase in MR. MR as high as $\sim 90\%$ is observed for thin film ($x = 0.05$) at $\mathbf{H} = 10$ kOe with $T_p = 100$ K while the corresponding bulk has a MR of only $\sim 43\%$. Low field MR in epitaxial thin films also display a pronounced anisotropy effect compared to bulk materials.

71.30.+h, 71.38.-k, 73.43.Qt, 75.30.Vn

Typeset using REVTeX

*corresponding author: scip0068@nus.edu.sg